

(19) World Intellectual Property Organization  
Internati nal Bureau



(43) International Publication Date  
30 November 2000 (30.11.2000)

PCT

(10) International Publication Number  
**WO 00/71607 A1**

(51) International Patent Classification<sup>7</sup>: C08G 77/442,  
A61K 7/06

(21) International Application Number: PCT/EP00/04429

(22) International Filing Date: 15 May 2000 (15.05.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
9912073.5 24 May 1999 (24.05.1999) GB

(71) Applicant (for AE, AU, BB, CA, CY, GB, GD, GH, GM, IE, IL, KE, LC, LK, LS, MN, MW, NZ, SD, SG, SL, SZ, TT, TZ, UG, ZA, ZW only): UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB).

(71) Applicant (for all designated States except AE, AU, BB, CA, CY, GB, GD, GH, GM, IE, IL, IN, KE, LC, LK, LS, MN, MW, NZ, SD, SG, SL, SZ, TT, TZ, UG, ZA, ZW): UNILEVER NV [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL).

(71) Applicant (for IN only): HINDUSTAN LEVER LIMITED [IN/IN]; Hindustan Lever House, 165/166 Backbay Reclamation, Maharashtra, Mumbai 400 020 (IN).

(72) Inventors: ADAMS, Gerald; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside CH63 3JW (GB). KHOSHDEL, Ezat; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside CH63 3JW (GB). MORETTA, Anthony; Unilever Research Port Sunlight, Quarry Road

East, Bebington, Wirral, Merseyside CH63 3JW (GB). PLANT, Yvonne, Christine; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside CH63 3JW (GB). REID, Euan, Stuart; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside CH63 3JW (GB).

(74) Agent: GRIFFITHS, Helen, Sarah; Unilever PLC, Patent Department, Colworth House, Sharnbrook, Bedford, Bedfordshire MK44 1LQ (GB).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- With international search report.
- Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POLYSILOXANE BLOCK COPOLYMERS IN TOPICAL COSMETIC AND PERSONAL CARE COMPOSITIONS

(57) Abstract: A process for making a polysiloxane block copolymer which is built up from units of the formula [A] [B], in which A is a polymeric block built up from radically polymerisable monomer, and B is a polysiloxane block, the process comprising the steps of polymerising a radically polymerisable monomer in the presence of an atom transfer radical initiator to form a polymer which is end-functionalised with a leaving group capable of nucleophilic substitution by nucleophilic end-groups on a polysiloxane, and reacting the polymer with a polysiloxane having nucleophilic end-groups so that a polysiloxane block copolymer is formed via a nucleophilic displacement reaction between the end-groups on the polysiloxane and leaving groups on the polymer respectively. Also provided is a cosmetic and personal care composition, such as a hair styling composition, comprising the polysiloxane block copolymer as described above.

WO 00/71607 A1

- 1 -

**POLYSILOXANE BLOCK COPOLYMERS IN TOPICAL COSMETIC AND  
PERSONAL CARE COMPOSITIONS**

5    Field of the Invention

The present invention relates to polysiloxane block copolymers suitable for use in cosmetic and personal care compositions, their preparation, and to cosmetic and  
10   personal care compositions, such as hair styling compositions, containing the polysiloxane block copolymers.

Background and Prior Art

15   Cosmetic and personal care compositions such as hair styling sprays, mousses, gels and shampoos, frequently contain resins, gums and adhesive polymers to provide a variety of benefits, for example, film-forming ability, thickening,  
sensory properties and hair shaping and setting.

20   Polymers for use in such compositions include organic or silicone-containing linear or graft copolymers which contain various monomers in an alternating, random, block or homopolymer configuration.

25   Graft copolymers are known for use as film-forming polymers in hair care and other personal care compositions. These graft copolymers typically comprise a polymeric backbone and one or more macromonomers grafted to the backbone, in which  
30   the physical and chemical attributes such as glass transition temperature and water solubility can be selected independently for the polymeric backbone and macromonomer

- 2 -

grafts in order to provide the desired overall polymer properties.

For example, WO95/01383 and WO95/01384 describe the use of  
5 water or alcohol soluble or dispersible graft copolymers in  
hair and skin care compositions, in which the copolymer has  
a backbone and two or more polymeric side chains, and is  
formed by copolymerisation of randomly repeating monomer  
units A and B. Monomer A is selected to have a hydrophobic  
10 character and macromonomer B comprises a long hydrophilic  
part. EP 412,704, EP 408,313 and EP 412,707 have suggested  
the use of silicone grafted acrylate copolymers in hair care  
applications. US 4,988,506 describes the use of non-pressure  
sensitive polysiloxane-grafted copolymers in hair care  
15 compositions.

Block copolymers have an advantage over graft copolymers in  
that the polymer architecture can be controlled more  
closely. This is particularly important when designing  
20 polymers with segments of distinct physical and chemical  
properties for particular applications, e.g. alternating  
"hard" and "soft" segments in a hairspray polymer for  
improved hold and feel.

25 US 5,468,477 describes cosmetics and personal care  
compositions containing a vinyl-silicone graft or block  
copolymer comprising a silicone polymer segment and a vinyl  
polymer segment. This block or graft copolymer is prepared  
by the free radical polymerisation of a mercapto functional  
30 silicone chain transfer agent and vinyl monomers. Copolymers  
prepared by this method generally have a low molecular  
weight and a low silicone content due to premature chain  
termination. Also, intramolecular cross-linking reactions

- 3 -

lead to polymer build up in an uncontrolled manner, and hence polydisperse systems with a mixture of chain lengths and molecular architectures. Furthermore, the presence of mercapto groups is a disadvantage in personal care applications since they tend to decompose to give odour problems.

Another approach to the synthesis of block copolymers is to use organopolysiloxane macroinitiators, which are organopolysiloxanes which contain groups which form radicals. These are described in US 5,523,365 and used in WO98/48771, where a polydimethylsiloxane macroinitiator with azo groups is used to synthesise a block copolymer. Problems include the expense and safety hazards associated with the radical macroinitiator, which has to be present in significant quantities, otherwise there will be insufficient siloxane content in the final product. Furthermore, the size of the polydimethylsiloxane macroinitiator means that the reaction is inefficient, and large quantities of unreacted silicone have to be removed in a time-consuming extraction process that would be extremely difficult to scale up.

A need exists for conveniently prepared and cost-effective polysiloxane block copolymers for use in cosmetics and personal care compositions.

The present invention provides an improved process for making polysiloxane block copolymers in which end-functionalised polymers are prepared using atom transfer radical polymerisation and then reacted with organopolysiloxanes using a simple nucleophilic displacement reaction, to prepare polysiloxane block copolymers of controlled architecture. Atom transfer radical

- 4 -

polymerisation is described in general in *Polymer* Vol 39, No.21, pp 5163-5170 (Nakagawa et al) and used in WO98/51261 to make graft copolymers.

## 5 Summary of the Invention

In a first aspect, the present invention provides a process for making a polysiloxane block copolymer which is built up from units of the formula [A][B], in which A is a polymeric  
10 block built up from radically polymerisable monomer, and B is a polysiloxane block, the process comprising the steps of polymerising a radically polymerisable monomer in the presence of an atom transfer radical initiator to form an polymer which is end-functionalised with a leaving group  
15 capable of nucleophilic substitution by nucleophilic end-groups on a polysiloxane; and reacting the polymer with a polysiloxane having nucleophilic end-groups so that a polysiloxane block copolymer is formed via a nucleophilic displacement reaction between the end-groups on the  
20 polysiloxane and leaving groups on the polymer respectively.

In a second aspect, the invention provides a polysiloxane block copolymer which is obtainable by the process described above.

25

The invention also provides a cosmetic and personal care composition, such as a hair styling composition, comprising the polysiloxane block copolymer as described above.

30

- 5 -

Detailed Description and Preferred EmbodimentsProcess


- 5 The process of the present invention comprises two key reaction steps:

First reaction step

- 10 The first reaction step involves polymerising a radically polymerisable monomer in the presence of an atom transfer radical initiator to form an polymer which is end-functionalised with a leaving group capable of nucleophilic substitution by nucleophilic end-groups on a polysiloxane.
- 15 By "end-functionalised" and "end-group" is meant that the group is at or near a terminal position of the polymer and polysiloxane respectively.

Typically, the atom transfer radical initiator comprises at least one - C (O) X group, in which X is a leaving group capable of substitution by a nucleophilic O, N or S atom on the polysiloxane in the second reaction step, and at least one organic halide group capable of generating a radical in the presence of a transition metal catalyst.

25 Examples of preferred atom transfer radical initiators have the formula:




30 where  $R^1$  is the organic halide group and X is the leaving group. Preferably X is a halogen atom (F, Cl, Br or I). By "organic halide group" is meant any linear, branched or

- 6 -

cyclic (aromatic or otherwise) carbon structure, whether substituted or unsubstituted,, which also contains a halogen atom (F, Cl, Br or I).

5 Preferred radical initiators have the general formula:



where Hal' and Hal independently denote halogen atoms,  $R^2$  and  $R^3$  are independently selected from hydrogen or a monovalent,  
10 optionally substituted, linear or branched  $C_{1-18}$  hydrocarbon radical,  $r$  is an integer having a value of 0 or 1, and  $R^4$  is selected from divalent, optionally substituted, linear or branched  $C_1 - C_{18}$  hydrocarbon radicals.

15 Examples of monovalent, unsubstituted radicals are alkyl radicals, such as the methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, tert-butyl, n-pentyl, iso-pentyl, neo-pentyl and tert-pentyl radical; alkoxy radicals, such as the methoxy, ethoxy, n-propoxy, iso-propoxy, n-butoxy, iso-  
20 butoxy, tert-butoxy, n-pentoxy, iso-pentoxy, neo-pentoxy and tert-pentoxy radical; hexyl radicals, such as the n-hexyl radical; alkenyl radicals, such as the vinyl, allyl, 5-hexenyl, 4-vinylcyclohexyl and the 3-norbornenyl radical; cycloalkyl radicals, such as cyclopentyl, cyclohexyl, 4-ethylcyclohexyl and cycloheptyl radical; norbornyl radicals  
25 and methylcyclohexyl radicals; aryl radicals, such as the phenyl, biphenyl, naphthyl, anthryl and phenanthryl radical; alkaryl radicals, such as o-, m- and p-tolyl radical, xylyl radicals and ethylphenyl radical; and aralkyl  
30 radicals, such as the benzyl, styryl, and phenylethyl radicals.

- 7 -

Examples of monovalent, substituted radicals are halogenated hydrocarbon radicals, such as the chloromethyl, 3-chloropropyl, 3-bromopropyl, 3,3,3-trifluoropropyl and 5,5,5,4,4,3,3-heptafluoropentyl radical and the

5 chlorophenyl, dichlorophenyl and trifluorotolyl radical; mercaptoalkyl radicals, such as the 2-mercaptoethyl and 3-mercaptopropyl radical; cyanoalkyl radicals, such as the 2-cyanoethyl and 3-cyanopropyl radical; aminoalkyl radicals, such as the 3-aminopropyl, N-(2-aminoethyl)-3-aminopropyl

10 and N-(2-aminoethyl)-3-amino-(2-methyl)propyl radical; aminoaryl radicals, such as the aminophenyl radical; acyloxyalkyl radicals, such as the 3-acryloxypropyl and 3-methacryloxypropyl radical; and hydroxyalkyl radicals, such as the hydroxypropyl radical.

15

Preferred monovalent radicals are independently selected from C<sub>1</sub> to C<sub>6</sub> alkyl radicals or the phenyl radical, in particular the methyl, ethyl, propyl or phenyl radical.

20 Examples of divalent hydrocarbon radicals are linear or branched saturated alkylene radicals, such as the methylene and ethylene radical, as well as propylene, butylene, pentylene, hexylene, cyclohexylene and octadecylene radicals; alkoxyalkylene radicals such as the

25 methoxyethylene and ethoxyethylene radical; unsaturated alkylene or arylene radicals, such as the hexenylene radical and phenylene radicals; alkarylene radicals such as the methylphenylene and ethylphenylene radical, and

30 alkoxyarylene radicals such as the methoxyphenylene and ethoxyphenylene radical. The divalent hydrocarbon radical can be interrupted by divalent radicals, bonded to carbon atoms on both sides, such as -O-, -C(O)O-, -O(O)C-, -CONR<sup>5</sup>-, -NR<sup>5</sup>C(O)- and -C(O)-, where R<sup>5</sup> is hydrogen or a monovalent,



- 8 -

optionally substituted, linear or branched  $C_{1-18}$  hydrocarbon radical as described above.

A particularly preferred radical initiator corresponding to  
5 the above general formula has:

Hal and Hal' = Br,  $R^2$  and  $R^3$  = methyl and  $r = 0$ .

The first reaction step involves polymerising a radically  
10 polymerisable monomer in the presence of the atom transfer  
radical initiator. The reaction is catalysed by a Cu (I)  
salt or other transitional metal species. In this reaction  
step, the organic halide groups act as initiators in the  
presence of the radically polymerisable monomers and the  
15 catalyst, resulting in the linking of a block of radically  
polymerisable monomers onto the atom transfer radical  
initiator by atom transfer radical polymerisation. This  
block of radically polymerisable monomers constitutes the  
polymeric block (denoted A) of the polysiloxane block  
20 copolymer as described above. The product of the first  
reaction step is thus a polymer which is end-functionalised  
with a leaving group capable of nucleophilic substitution by  
nucleophilic end-groups on a polysiloxane.

25 The catalyst for the first reaction step is a transition  
metal salt, preferably a Cu(I) salt such as Cu(I) halide  
salts (Cl, F, Br, I) and which is preferably complexed to a  
ligand which is suitable for solubilising the Cu(I) salt in  
the reaction mixture. WO98/51261 describes preferred ligands  
30 for use in solubilising the Cu(I) salt in the reaction  
mixture (aprotic bidentates such as diphosphates, 2,2'  
bipyridyl,  $C_1$ - $C_{20}$  alkyl substituted bipyridyl and  
combinations thereof, most preferably 2,2' bipyridyl

- 9 -

complexed to a Cu(I) halide salt, in particular CuCl).  
WO98/51262 also refers to several journal articles which  
describe examples of the polymerisation process (atom  
transfer radical polymerisation) used in the second reaction  
5 step of the process of the present invention. Further  
examples of such descriptions can be found in *Polymer* Vol  
39, No.21, pp 5163-5170 (Nakagawa et al) and *Macromolecules*  
1997, 30, 2190-2193 (Haddleton et al). Those skilled in the  
art would understand that a variety of other ligands can  
10 also be employed.

The polymerisation process of the first reaction step can be  
furnished in bulk, solution, emulsion and suspension, as  
would be understood by those skilled in the art.

15

Radically polymerisable monomers suitable for use in the  
first reaction step of the process of the present invention  
are preferably ethylenically unsaturated monomers.

20 By "polymerisable" is meant monomers that can be polymerised  
in accordance with the second reaction step of the process  
of the present invention using atom transfer radical  
polymerisation, more preferably "living" atom transfer  
radical polymerisation, in which polymer chain length and  
25 architecture can be controlled via stability of the radical,  
thus leading to improved monodispersity.

By "ethylenically unsaturated" is meant monomers that  
contain at least one polymerisable carbon-carbon double bond  
30 (which can be mono-, di-, tri- or tetra -substituted).  
Either a single monomer or a combination of two or more  
monomers can be utilised. In either case, the monomers are

- 10 -

selected to meet the physical and chemical requirements of the final polysiloxane block copolymer.

Suitable ethylenically unsaturated monomers have the  
5 following general formula:



in which  $R^6$  and  $R^7$  are independently selected from hydrogen,  
10  $C_1 - C_{10}$  straight or branched chain alkyl, methoxy, ethoxy, 2-hydroxyethoxy, 2-methoxyethyl and 2-ethoxyethyl groups;

$G$  is selected from hydroxyl,  $-O(M)_{2/v}$ ,  $-OR^8$ ,  $-NH_2$ ,  $-NHR^8$  and  
15  $-N(R^8)(R^9)$ ;

where  $M$  is a counter-ion of valency  $v$  selected from metal ions such as alkali metal ions and alkaline earth metal ions, ammonium ions and substituted ammonium ions such as mono-, di-, tri- and tetraalkylammonium ions, and each  $R^8$  and  
20  $R^9$  is independently selected from hydrogen,  $C_1 - C_8$  straight or branched chain alkyl,  $N,N$ -dimethylaminoethyl, 2-hydroxyethyl, 2-methoxyethyl, and 2-ethoxyethyl.  
Representative non-limiting examples of monomers useful herein include protected or non-protected acrylic acid and  
25 methacrylic acid and salts, esters and amides thereof.

The salts can be derived from any of the common non-toxic metal, ammonium, or substituted ammonium counter ions. The esters can be derived from  $C_{1-40}$  straight chain,  $C_{3-40}$  branched  
30 chain, or  $C_{3-40}$  carbocyclic alcohols, from polyhydric alcohols having from about 2 to about 8 carbon atoms and from about 2 to about 8 hydroxyl groups (non-limiting examples of which include ethylene glycol, propylene glycol, butylene glycol,

- 11 -

hexylene glycol, glycerol, and 1,2,6-hexanetriol); from amino alcohols (non-limiting examples of which include aminoethanol, dimethylaminoethanol and diethylaminoethanol and their quaternised derivatives); or from alcohol ethers  
5 (non-limiting examples of which include methoxyethanol and ethoxyethanol).

The amides can be unsubstituted, N-alkyl or N-alkylamino mono-substituted, or N,N-dialkyl, or N,N-dialkylamino  
10 disubstituted, wherein the alkyl or alkylamino groups can be derived from C<sub>1-40</sub> straight chain, C<sub>3-40</sub> branched chain, or C<sub>3-40</sub> carbocyclic moieties. In addition, the alkylamino groups can be quaternised. Also useful as monomers are protected and unprotected acrylic or/and methacrylic acids,  
15 salts, esters and amides thereof, wherein the substituents are on the two and three carbon position of the acrylic and/or methacrylic acids, and are independently selected from C<sub>1-4</sub> alkyl, hydroxyl, halide (-Cl, -Br, -F, -I), -CN, and -CO<sub>2</sub>H, for example methacrylic acid, ethacrylic acid, alpha-  
20 chloroacrylic acid and 3-cyano acrylic acid. The salts, esters, and amides of these substituted acrylic and methacrylic acids can be defined as described above for the acrylic/methacrylic acid salts, esters and amides. Other useful monomers include vinyl and allyl esters of C<sub>1-40</sub>  
25 straight chain, C<sub>3-40</sub> branched chain, or C<sub>3-40</sub> carbocyclic carboxylic acids, vinyl and allyl halides (e.g. vinyl chloride, allyl chloride), (e.g. vinyl pyridine, allyl pyridine); vinylidene chloride; and hydrocarbons having at least one unsaturated carbon-carbon double bond (e.g.  
30 styrene, alpha-methylstyrene, t-butylstyrene, butadiene, isoprene, cyclohexadiene, ethylene, propylene, 1-butene, 2-butene, isobutylene, p-methylstyrene); and mixtures thereof.

- 12 -

Preferred monomers useful herein include those selected from protected and unprotected acrylic acid, methacrylic acid, ethacrylic acid, methyl acrylate, ethyl acrylate, n-butyl acrylate, iso-butyl acrylate, t-butyl acrylate, 2-ethylhexyl acrylate, decyl acrylate, octyl acrylate, methyl methacrylate, ethyl methacrylate, n-butyl methacrylate, iso-butyl methacrylate, t-butyl methacrylate, 2-ethylhexyl methacrylate, decyl methacrylate, methyl ethacrylate, ethyl ethacrylate, n-butyl ethacrylate, iso-butyl ethacrylate, t-butyl ethacrylate, 2-ethylhexyl ethacrylate, decyl ethacrylate, 2,3-dihydroxypropyl acrylate, 2,3-dihydroxypropyl methacrylate, 2-hydroxyethyl acrylate, 2-hydroxypropyl acrylate, hydroxypropyl methacrylate, glyceryl monoacrylate, glyceryl monoethacrylate, glycidyl methacrylate, glycidyl acrylate, acrylamide, methacrylamide, ethacrylamide, N-methyl acrylamide, N,N-dimethyl acrylamide, N,N-dimethyl methacrylamide, N-ethyl acrylamide, N-isopropyl acrylamide, N-butyl acrylamide, N-t-butyl acrylamide, N,N-di-n-butyl acrylamide, N,N-diethylacrylamide, N-octyl acrylamide, N-octadecyl acrylamide, N,N-diethylacrylamide, N-phenyl acrylamide, N-methyl methacrylamide, N-ethyl methacrylamide, N-dodecyl methacrylamide, N,N-dimethylaminoethyl acrylamide, quaternised N,N-dimethylaminoethyl acrylamide, N,N-dimethylaminoethyl methacrylamide, quaternised N,N-dimethylaminoethyl methacrylamide N,N-dimethylaminoethyl acrylate, N,N-dimethylaminoethyl methacrylate, quaternised N,N-dimethylaminoethyl aminoethyl acrylate, quaternised N,N-dimethylaminoethyl methacrylate, 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylate, 2-hydroxyethyl ethacrylate, glyceryl acrylate, 2-methoxyethyl acrylate, 2-methoxyethyl methacrylate, 2-methoxyethyl ethacrylate, 2-ethoxyethyl acrylate, 2-ethoxyethyl methacrylate, 2-ethoxyethyl ethacrylate, maleic

- 13 -

acid, maleic anhydride and its half esters, fumaric acid, itaconic acid, itaconic anhydride and its half esters, crotonic acid, angelic acid, diallyldimethyl ammonium chloride, vinyl pyrrolidone vinyl imidazole, methyl vinyl  
5 ether, methyl vinyl ketone, maleimide, vinyl pyridine, vinyl furan, styrene sulphonate, allyl alcohol, allyl citrate, allyl tartrate, vinyl acetate, vinyl alcohol, vinyl caprolactam and mixtures thereof.

10 More preferred monomers are those selected from methyl acrylate, methyl methacrylate, methyl ethacrylate, ethyl acrylate, ethyl methacrylate, ethyl ethacrylate, n-butyl acrylate, n-butyl methacrylate, n-butyl ethacrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, 2-ethylhexyl  
15 ethacrylate, N-octyl acrylamide, 2-methoxyethyl acrylate, 2-hydroxyethyl acrylate, N,N-dimethylaminoethyl acrylate, N,N-dimethylaminoethyl methacrylate, acrylic acid, methacrylic acid, 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylate and mixtures thereof.

20 Most preferred monomers are those selected from N,N-dimethylaminoethyl acrylate, N,N-dimethylaminoethyl methacrylate, 2-ethylhexyl acrylate, hydroxyethyl methacrylate, N-octyl acrylamide, 2-hydroxyethyl acrylate,  
25 2-hydroxyethyl methacrylate and mixtures thereof.


#### Second reaction step

The second reaction step involves reacting the polymer  
30 obtained from the first reaction step with a polysiloxane having nucleophilic end-groups.

- 14 -

The polysiloxane having nucleophilic end-groups may be linear, branched or hyperbranched, provided it has at least one nucleophilic end-group as described above. Typically such an end-group is one capable of nucleophilic attack via its O, N or S atom.

Examples of preferred polysiloxanes have the formula:



in which n is an integer of 5 to 1,000,000;

$R^{10}$  and  $R^{11}$  are independently selected from monovalent, optionally substituted, linear or branched  $C_{1-18}$  hydrocarbon radicals as described above,

$R^{12}$  and  $R^{13}$  are independently selected from divalent, optionally substituted, linear or branched  $C_1 - C_{18}$  hydrocarbon radicals as described above;

p and q are integers having a value of 0 or 1, and

Y and Z are independently selected from hydroxyl,  $-NH_2$  and  $-NHR^{14}$  where  $R^{14}$  is a monovalent, optionally substituted, linear or branched  $C_{1-18}$  hydrocarbon radical as described above. Either, but not both, of Y and Z may also be hydrogen or a monovalent, optionally substituted, linear or branched  $C_{1-18}$  hydrocarbon radical as described above, thereby giving a mono-end-capped polysiloxane.

Particularly preferred polysiloxanes corresponding to the above general formula have:

- 15 -

$n = 5$  to 1,000,000, preferably 5 to 500;

$R^{10}$  and  $R^{11}$  = methyl,

$p$  and  $q = 0$  and  $Y$  and  $Z$  = hydroxyl; or  $p$  and  $q = 1$ ,  $R^{12}$  and

5  $R^{13} = (CH_2)_3$  and  $Y$  and  $Z = NH_2$ .

In the second reaction step, a polysiloxane block copolymer is formed via a nucleophilic displacement reaction between the end-groups on the polysiloxane and leaving groups on the  
10 polymer respectively.





The nucleophilic displacement reaction of the second reaction step may be carried out under conventional reaction conditions.

15

#### Polysiloxane Block Copolymers


A typical polysiloxane block copolymer obtainable by the process described above is built up from units of the  
20 general formula  $[A]L[B]$ , in which  $A$  is a polymeric block built up from radically polymerisable monomer,  $B$  is a polysiloxane block and  $L$  is a divalent linker group which links the  $A$  and  $B$  blocks via O-Si, N-Si or S-Si bonds to the  $B$  block. Preferably  $L$  is selected from:

25





- 16 -



in which  $R^{15}$  is a divalent, optionally substituted, linear or branched  $C_1 - C_{18}$  hydrocarbon radical as described above, and

5

$R^{16}$  and  $R^{17}$  are independently selected from monovalent, optionally substituted, linear or branched  $C_{1-18}$  hydrocarbon radicals as described above.

10 The overall molecular architecture of the silicone block copolymers of the invention can be described by the formulas A-L-B, A-L-B-L-A,  $-(A-L-B)_n-$ , wherein n is an integer of 2 or greater, or  $[A-L-][A-L-]B[-L-A][-L-A]$ , wherein A-L-B represents a diblock structure, A-L-B-L-A represents a  
15 triblock structure,  $-(A-L-B)_n-$  represents a multiblock structure, and  $[A-L-][A-L-]B[-L-A][-L-A]$  represents a dendritic structure.

## 20 Cosmetic and Personal Care Compositions

The polysiloxane block copolymers of the present invention are preferably formulated into hair care compositions, especially hairspray compositions, but can also be  
25 formulated into a wide variety of product types, including mousses, gels, lotions, tonics, sprays, shampoos, conditioners, rinses, hand and body lotions, facial moisturisers, sunscreens, anti-acne preparations, topical analgesics, mascaras, and the like. The carriers and  
30 additional components required to formulate such products vary with product type and can be routinely chosen by one skilled in the art. The following is a description of some of these carriers and additional components.

- 17 -

Carriers

Hair care compositions of the present invention can comprise a carrier, or a mixture of such carriers, which are suitable for application to the hair. The carriers are present at from about 0.5% to about 99.5%, preferably from about 5.0% to about 99.5%, more preferably from about 10.0% to about 98.0%, of the composition. As used herein, the phrase "suitable for application to hair" means that the carrier does not damage or negatively affect the aesthetics of hair or cause irritation to the underlying skin. Carriers suitable for use with hair care compositions of the present invention include, for example, those used in the formulation of hair sprays, mousses, tonics, gels, shampoos, conditioners, and rinses. The choice of appropriate carrier will also depend on the particular copolymer to be used, and whether the product formulated is meant to be left on the surface to which it is applied (e.g., hair spray, mousse, tonic, or gel) or rinsed off after use (e.g., shampoo, conditioner, rinse).

The carriers used herein can include a wide range of components conventionally used in hair care compositions. The carriers can contain a solvent to dissolve or disperse the particular copolymer being used, with water, the C1-C6 alcohols, lower alkyl acetate and mixtures thereof being preferred. The carriers can also contain a wide variety of additional materials such as acetone, hydrocarbons (such as isobutane, hexane, decene), halogenated hydrocarbons (such as Freons) and volatile silicon derivatives such as cyclomethicone. When the hair care composition is a hair spray, tonic, gel, or mousse the preferred solvents include water, ethanol, volatile silicone

- 18 -

derivatives, and mixtures thereof. The solvents used in such mixtures may be miscible or immiscible with each other. Mousses and aerosol hair sprays can also utilise any of the conventional propellants to deliver the material as a foam (in the case of a mousse) or as a fine, uniform spray (in the case of an aerosol hair spray). Examples of suitable propellants include materials such as trichlorofluoromethane, dichlorodifluoromethane, difluoroethane, dimethylether, propane, n-butane or isobutane. A tonic or hair spray product having a low viscosity may also utilise an emulsifying agent. Examples of suitable emulsifying agents include nonionic, cationic, anionic surfactants, or mixtures thereof. If such an emulsifying agent is used, it is preferably present at a level of from about 0.01% to about 7.5% of the composition. The level of propellant can be adjusted as desired but is generally from about 3% to about 30% of mousse compositions and from about 15% to about 50% of the aerosol hair spray compositions.

Suitable spray containers are well known in the art and include conventional, non-aerosol pump sprays i.e., "atomisers, " aerosol containers or cans having propellant, as described above, and also pump aerosol containers utilising compressed air as the propellant.

Where the hair care compositions are conditioners and rinses the carrier can include a wide variety of conditioning materials. Where the hair care compositions are shampoos, the carrier can include, for example, surfactants, suspending agents, and thickeners.

- 19 -

The carrier can be in a wide variety of forms. For example, emulsion carriers, including oil-in-water, water-in-oil, water-in-oil-in-water, and oil-in-water-in-silicone emulsions, are useful herein. These emulsions can cover a broad range of viscosities, e.g., from about 100 cps to about 200,000 cps. These emulsions can also be delivered in the form of sprays using either mechanical pump containers or pressurised aerosol containers using conventional propellants. These carriers can also be delivered in the form of a mousse. Other suitable topical carriers include anhydrous liquid solvents such as oils, alcohols, and silicones (e.g., mineral oil, ethanol, isopropanol, dimethicone, cyclomethicone, and the like); aqueous-based single phase liquid solvents (e.g., hydro-alcoholic solvent systems); and thickened versions of these anhydrous and aqueous-based single phase solvents (e.g., where the viscosity of the solvent has been increased to form a solid or semi-solid by the addition of appropriate gums, resins, waxes, polymers, salts, and the like).

20

#### Additional Components

A wide variety of additional components can be employed in cosmetic and personal care compositions according to the present invention. Examples include the following:

25

-       sunscreening agents such as 2-ethylhexyl p-methoxycinnamate, 2-ethylhexyl N,N-dimethyl-p-aminobenzoate, p-aminobenzoic acid, 2-phenylbenzimidazole-5-sulfonic acid, octocrylene, oxybenzone, homomenthyl salicylate, octyl salicylate, 4,4'-methoxy-t-butylidibenzoylmethane, 4-isopropyl dibenzoylmethane, 3-benzylidene camphor, 3-(4-methylbenzylidene) camphor,

30

- 20 -

titanium dioxide, zinc oxide, silica, iron oxide, and mixtures thereof.

- anti-dandruff actives such as zinc pyrithione,  
5 piroctone olamine, selenium disulphide, sulphur, coal tar, and the like.

- conditioning agents for hair care compositions such as hydrocarbons, silicone fluids, and cationic materials. The  
10 hydrocarbons can be either straight or branched chain and can contain from about 10 to about 16, preferably from about 12 to about 16 carbon atoms. Examples of suitable hydrocarbons are decane, dodecane, tetradecane, tridecane, and mixtures thereof. Examples of suitable silicone  
15 conditioning agents useful herein can include either cyclic or linear polydimethylsiloxanes, phenyl and alkyl phenyl silicones, and silicone copolyols. Cationic conditioning agents useful herein can include quaternary ammonium salts or the salts of fatty amines.

20

- surfactants for hair shampoo and conditioner compositions. For a shampoo, the level is preferably from about 10% to about 30%, preferably from 12% to about 25%, of the composition. For conditioners, the preferred level of  
25 surfactant is from about 0.2% to about 3%. Surfactants useful in compositions of the present invention include anionic, nonionic, cationic, zwitterionic and amphoteric surfactants.

30 - carboxylic acid polymer thickeners. These crosslinked polymers contain one or more monomers derived from acrylic acid, substituted acrylic acids, and salts and esters of these acrylic acids and the substituted acrylic

- 21 -

acids, wherein the crosslinking agent contains two or more carbon-carbon double bonds and derived from a polyhydric alcohol. Examples of carboxylic acid polymer thickeners useful herein are those selected from the group consisting of carbomers, acrylates/C10-C30 alkyl acrylate crosspolymers, and mixtures thereof. Compositions of the present invention can comprise from about 0.025% to about 1%, more preferably from about 0.05% to about 0.75% and most preferably from about 0.10% to about 0.50% of the carboxylic acid polymer thickeners.

- emulsifiers for emulsifying the various carrier components of the compositions of the invention. Suitable emulsifier types include polyethylene glycol 20 sorbitan monolaurate (Polysorbate 20), polyethylene glycol 5 soya sterol, Steareth-20, Cetareth-20, PPG-2 methyl glucose ether distearate, Ceteth-10, Polysorbate 80, cetyl phosphate, potassium cetyl phosphate, diethanolamine cetyl phosphate, Polysorbate 60, glyceryl stearate, PEG-100 stearate, and mixtures thereof. The emulsifiers can be used individually or as a mixture of two or more and can comprise from about 0.1% to about 10%, more preferably from about 1% to about 7%, and most preferably from about 1% to about 5% of the compositions of the present invention.

- vitamins and derivatives thereof (e.g., ascorbic acid, vitamin E, tocopheryl acetate, retinoic acid, retinol, retinoids, and the like.

- cationic polymers (e.g., cationic guar gum derivatives such as guar hydroxypropyltrimonium chloride and hydroxypropyl guar hydroxypropyltrimonium chloride, available as the Jaguar C series from Rhone-Poulenc).

- 22 -

- preservatives, antioxidants, chelators and sequestrants;  
and aesthetic components such as fragrances, colourings,  
hair nutrients and essential oils.

- 5 The invention will now be illustrated by the following non-limiting Examples:

- 23 -

EXAMPLE

A silicone block copolymer was prepared by the following process:

5

Step 1

Cu<sup>I</sup>Br (0.0852g, 0.594mmol) along with a magnetic stirrer bar was placed in a dry Schlenk flask which was then evacuated and flushed with nitrogen three times. 2-dimethylaminoethyl methacrylate (DMAEMA) (5.0mL, 0.030moles), toluene (7.2mL) and 2-bromoisobutyryl bromide (0.15 mL, 1.19 mmol) were added to the Schlenk using degassed syringes.\* The solution was then deoxygenated by three freeze-pump-thaw cycles. Finally, once the flask had reached the desired reaction temperature of 90°C the "propyl-2-pyridinalmethanimine ligand (1) (0.20mL, 1.19mmol) was added with stirring. The reaction mixture immediately turned dark brown in colour on addition of the ligand. The polymerisation reaction was carried out for eight hours.

The monomer was purified by passing down a basic alumina column prior to use and purged with nitrogen for at least one hour. Toluene, which was used as a solvent for all polymerisations, was also degassed in this manner. Cu<sup>I</sup>Br was purified before use according to a published procedure.<sup>1</sup>

1) Keller, R. N.; Wycoff, H. D. *Inorganic Synthesis*, 1947, 2, 1.

30

The product was purified by a conventional dissolution and precipitation method (three times). It had GPC molecular weight of Mn 4,300, Mw 5,200, D 1.18.



- 24 -

Step 2

Poly(dimethyl siloxane) containing hydroxyl groups at both ends (5.6 g, molecular weight 15,000) was dissolved in  
5 toluene (100 mL). To this solution, 4-  
dimethylaminopropylpyridine (0.26 mmol, 0.031 g) was added.  
Then a solution of the product prepared in Step 1 (3.2g, Mw  
5,200) in toluene (100ml) was added dropwise over one hour.  
The reaction was left overnight at room temperature. The  
10 reaction mixture was warmed to 50 °C for two more hours to  
drive the esterification reaction to completion. The solvent  
was removed under vacuum to yield the block copolymer.

The resultant block copolymer (ABA triblock structure) had a  
15 controlled molecular weight and narrow polydispersity.

Tests showed that the copolymer had excellent film-forming,  
bond strength and sensory properties when formulated into a  
hairspray.

- 25 -

CLAIMS

1. A process for making a polysiloxane block copolymer which is built up from units of the formula [A][B], in which A is  
5 a polymeric block built up from radically polymerisable monomer, and B is a polysiloxane block, the process comprising the steps of polymerising a radically polymerisable monomer in the presence of an atom transfer radical initiator to form a polymer which is end-  
10 functionalised with a leaving group capable of nucleophilic substitution by nucleophilic end-groups on a polysiloxane, and reacting the polymer with a polysiloxane having nucleophilic end-groups so that a polysiloxane block copolymer is formed via a nucleophilic displacement reaction  
15 between the end-groups on the polysiloxane and leaving groups on the polymer respectively.

2. A process according to claim 1, comprising the steps of:

20 (i) reacting an atom transfer radical initiator, comprising at least one -C(O)X group, in which X is a leaving group capable of substitution by a nucleophilic O, N or S atom on a polysiloxane and at least one organic halide group capable of generating a radical in the presence of a  
25 transition metal catalyst, with radically polymerisable monomers to form a polymer which is end-functionalised with a leaving group capable of nucleophilic substitution by nucleophilic end-groups on the polysiloxane, and

30 (ii) reacting the polymer obtained from (i) with a polysiloxane having nucleophilic end-groups so that a polysiloxane block copolymer is formed via a nucleophilic

- 26 -

displacement reaction between the end-groups on the polysiloxane and leaving groups on the polymer respectively.

3. A polysiloxane block copolymer obtainable by the process  
5 of claim 1 or 2.

4. A polysiloxane block copolymer according to claim 3,  
which is built up from units of the general formula [A]L[B],  
in which A is a polymeric block built up from radically  
10 polymerisable monomer, B is a polysiloxane block and L is a  
divalent linker group which links the A and B blocks via O-Si,  
N-Si or S-Si bonds to the B block, and which is preferably  
selected from:

15 - R<sup>15</sup> - C (O) - O - ;

- R<sup>15</sup> - O - C (O) - O - ;

- R<sup>15</sup> - C (O) - N(R<sup>16</sup>) - ;

20

- R<sup>15</sup> - O - C(O) - N (R<sup>16</sup>) - , or

- R<sup>15</sup> - N (R<sup>16</sup>) - C(O) - N (R<sup>17</sup>) - ;

25 in which R<sup>15</sup> is a divalent, optionally substituted, linear or  
branched C<sub>1</sub> - C<sub>18</sub> hydrocarbon radical, and

R<sup>16</sup> and R<sup>17</sup> are independently selected from monovalent,  
optionally substituted, linear or branched C<sub>1-18</sub> hydrocarbon  
30 radicals.

- 27 -

5. A cosmetic and personal care composition comprising the polysiloxane block copolymer of claim 3 or 4.

6. A cosmetic and personal care composition according to  
5 claim 5, which is formulated as a hairspray, gel or mousse.

PCT/EP 00/04429

According to International Patent Classification (IPC) or to both national classification and IPC

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**EPO-Internal, WPI Data, PAJ**

### C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 01480 A (UNIV CARNEGIE MELLON) 15 January 1998 (1998-01-15) claims 1,8,23,27  —	1
A	WO 98 51261 A (PROCTER & GAMBLE) 19 November 1998 (1998-11-19) cited in the application claim 1  —  —/—	1

**Y** Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "Z" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

**20 September 2000**

04/10/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3018

Authorized officer

Depi jper, R

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/04429

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	NAKAGAWA Y ET AL: "Development of novel attachable initiators for atom transfer radical polymerization. Synthesis of block and graft copolymers from poly(dimethylsiloxane) macroinitiators" POLYMER,GB,ELSEVIER SCIENCE PUBLISHERS B.V, vol. 39, no. 21, 1 October 1998 (1998-10-01), pages 5163-5170, XP004139649 ISSN: 0032-3861 * whole article *	1
A	WO 98 48771 A (PROCTER & GAMBLE) 5 November 1998 (1998-11-05) cited in the application claims 1,4-10 page 5, paragraphs 1,3 page 12, paragraph 2 -page 13, paragraph 3	1
P,A	EP 0 992 519 A (KANEGAFUCHI CHEMICAL IND) 12 April 2000 (2000-04-12) claims 1-32 page 5, paragraph 45 page 6, paragraph 56 -page 13, paragraph 76	1

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/04429

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9801480 A	15-01-1998	US 5789487 A AU 3585997 A BR 9710273 A CA 2259995 A CN 1228789 A EP 0914352 A US 5945491 A	04-08-1998 02-02-1998 10-08-1999 15-01-1998 15-09-1999 12-05-1999 31-08-1999
WO 9851261 A	19-11-1998	AU 7073798 A EP 0977540 A ZA 9804087 A	08-12-1998 09-02-2000 16-11-1998
WO 9848771 A	05-11-1998	AU 7160598 A CN 1259033 T EP 0977542 A US 6074628 A ZA 9803498 A	24-11-1998 05-07-2000 09-02-2000 13-06-2000 29-10-1998
EP 0992519 A	12-04-2000	WO 9955751 A JP 2000198825 A	04-11-1999 18-07-2000